

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188	
The public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing the burden, to the Department of Defense, Executive Service Directorate (0704-0188). Respondents should be aware that notwithstanding any other provision of law, no person shall be subject to any penalty for failing to comply with a collection of information if it does not display a currently valid OMB control number.					
PLEASE DO NOT RETURN YOUR FORM TO THE ABOVE ORGANIZATION.					
1. REPORT DATE (DD-MM-YYYY) 26-02-2008		2. REPORT TYPE Final		3. DATES COVERED (From - To) 20020701 - 20071031	
4. TITLE AND SUBTITLE -				5a. CONTRACT NUMBER N00014-02-1-0801	
				5b. GRANT NUMBER	
				5c. PROGRAM ELEMENT NUMBER	
				5d. PROJECT NUMBER	
6. AUTHOR(S) Anthony G. Evans				5e. TASK NUMBER	
				5f. WORK UNIT NUMBER	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) The Regesnts of the University of California Santa Barbara The Office of Research Cheadle Hall Room 3227 Santa Barbara, CA 93106-2050				8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Office of Naval Research 875 North Randolph Street Arlington, VA 22203-1995				10. SPONSOR/MONITOR'S ACRONYM(S) ONR	
				11. SPONSOR/MONITOR'S REPORT NUMBER(S)	
12. DISTRIBUTION/AVAILABILITY STATEMENT <div style="text-align: center; margin-left: 150px;"> DISTRIBUTION STATEMENT A: Approved for Public Release Distribution Unlimited </div>					
13. SUPPLEMENTARY NOTES <div style="display: flex; justify-content: space-between;"> Project Description MULTIDISCIPLINARY UNIVERSITY RESEARCH INITIATIVE ON THE SCIENCE UNDERPINNING PRIME RELIANT COATINGS </div>					
14. ABSTRACT					
15. SUBJECT TERMS					
16. SECURITY CLASSIFICATION OF:			17. LIMITATION OF ABSTRACT		18. NUMBER OF PAGES
a. REPORT	b. ABSTRACT	c. THIS PAGE			19a. NAME OF RESPONSIBLE PERSON Anthony G. Evans
					19b. TELEPHONE NUMBER (include area code) (805) 893-7839

Oxide coatings in aero-turbine engines

Final Report

Submitted to:
Office of Naval Research

Dr. David Shifler

By
John W. Hutchinson
Harvard University
February 28, 2008

20080228266

Executive Summary

Oxide coatings used for various components in the hot section of aero-turbine engines experience temperature gradients at various stages during their flight cycle. One gradient exists during steady-state, due to the combination of the combustion environment next to the free surface and internal cooling of the underlying superalloy substrate. Other gradients develop during cooling of the surface when engine power is reduced. It is argued that deep delaminations, when observed within the oxide layer, can only be explained by the presence of a significant stress gradient in the coating, governed by these thermal circumstances. Two extreme cool-down scenarios are addressed. In one, the surface is cooled suddenly to a lower temperature, followed by slow uniform cooling. In the other, the entire system reduces its temperature uniformly before the temperature gradient in the TBC is eliminated. Criteria for guarding against delaminations within the oxide layer and along the interface with the substrate are provided and the outcome visualized in the form of delamination maps. A comparison with engine experience has provided a preliminary assessment of the relevant thermal scenarios.

Sub-surface delaminations have also been investigated under conditions of high thermal flux. A crack disrupts the heat flow thereby inducing crack tip stress intensities that can become critical. A complete parametric dependence of the energy release rate, G , and mode mix is presented in terms of the ratio of the crack length to its depth below the surface. Proximity to the surface elevates the local temperature, which in turn, significantly increases the crack driving force. A detailed assessment reveals that the energy release rates induced are capable of extending sub-surface delaminations, but only when the modulus has been elevated by either CMAS penetration or sintering. Otherwise, G remains well below the toughness.